

icobit



Program srl

Italy, 66100 Chieti Scalo - Via Custoza, 29
Reg. Imprese CH - C.F. 01459350680
P.Iva IT01887710695 - REA - CH 135733
Tel. +39.0871.5870.1- Fax +39.0871.562191
www.icobit.com - info@programsrl.it

SINCERT

ISO 9001

BUREAU VERITAS
Certification

N° 206859



TECHNICAL DATA SHEET: **ICOALL W**

PRODUCT DESCRIPTION

ICOALL is a protective paint made of synthetic resins, aluminium pigments in water emulsion emulsion.

ISSUE

- ◆ Painting of bitumen-polymer membranes and bitumen coats for general coverings made to protect them against ultra-violet rays.

PERFORMANCES

- ◆ Ultra-violet rays reflecting agent.
- ◆ Ultra-violet rays aggression resistance.
- ◆ Easy to apply.
- ◆ Solvent free – Environment friend

NOTES

- ◆ Apply ICOALL W at working temperatures between +5°C and +40°C.
- ◆ Wait for new bitumen-polymer membranes maturation (minimum three months) before proceeding to paint with ICOALL W because an efflorescence of oils contained could cause the detachment of product or “crocodile effect”.
- ◆ Before the application, mix the product, homogenizing the eventual deposit in the tin.
- ◆ Don't apply ICOALL W onto surfaces where water is stagnating.
- ◆ Don't apply ICOALL W with risk of rain, dew and/or fog

SURFACE PREPARATION

Carry out a careful cleaning of the surface, removing any protective paint which is peeling off.

APPLICATION INSTRUCTIONS

Apply two coats of ICOALL W with a consumption of 125÷150 gr/m² for each coat.

APPLICATION METHOD

Airless, roller, brush.

icobit**Program srl**

Italy, 66100 Chieti Scalo - Via Custozza, 29
 Reg. Imprese CH - C.F. 01459350680
 P.Iva IT01887710695 - REA - CH 135733
 Tel. +39,0871.5870.1- Fax +39,0871.562191
 www.icobit.com - info@programsrl.it

SINCERT

ISO 9001

BUREAU VERITAS
Certification

N° 206858



PRODUCT INFORMATION	VALUE	MEAS. UNIT
Type of product	single-component	
Specific gravity	1,05 (± 0,05)	Kg/lt
Solid content (weight)	20,5 (±2%)	%
Ford cup viscosity Ø 4mm	23 (±1)	Seconds
Application temperature	5-40	°C
Complete drying at 23°C ±3°C	60 (each coat)	Minutes
Suggested coats	2	n.
Consumption for each coat	0,125-0,150	Kg/m ²
Yield	3,3-4	m ² /Kg
Thickness of dried film	0,058 (for a consumption of 0,300 Kg/m ²)	mm
Dilution	Ready to use	
Colour	Metallic aluminium	
Shelf life	1	Year

CERTIFICATIONS

- Certifications resulted from our specified laboratory tests.

SAFETY STANDARDS

Risk phrases: not applicable
 Warnings: not applicable
 Symbols: not applicable

TRANSPORT

- ADR/RID land conveyance: no restrictions
- Customs code: 3209 (Paints and Varnishes base with syntetic polymers water base).

STORAGE

- Keep the product in dry and ventilated places.

PACKAGE

- plastic containers -DRUMS- 16 Litres.

Our technical service will meet any customer's requirements.

Please call us at 0871/58701 or, if you wish, visit our internet site: WEB SITE: <http://www.programsrl.it> – e-mail: info@programsrl.it.

All data refer to the standards in force at the time of issue. Program reserves the right to change them without prior notice. All data provided have been gathered from our practical experience and are test averages. Despite their reliability they do not constitute commitment and responsibility on the part of Program srl.

The buyer and user are responsible for the product suitability to its usage.