

PinTura

Cenomast Semi Gloss

For a smooth semi gloss finish



PinTura Cenomast Semi Gloss is a high quality acrylic copolymer based emulsion paint with outstanding washability, hiding power and colour retention properties. It has a good flow and gives a smooth, durable semigloss finish.

Recommended Substrates

 PinTura Cenomast Semi Gloss is suitable for most surfaces i.e. concrete, plaster, masonry, brickwork, gypsum, asbestos, cement and hard wooden boards.

Technical Data

| Colour | As per Conmix Paints shade card |
|--------------------------------|---------------------------------|
| Finish, Dry Film | Smooth / Semigloss |
| Specific gravity (ASTM D 1475) | 1.15 - 1.25 |
| Volume of Solids (Theoretical) | 44 ± 2% |
| Theoretical coverage* | 7 – 11 m²/ltr @ 110 microns wft |
| Wet Film Thickness Per Coat | 90 - 140 microns |
| Drying Time @ 25°C | Surface dry: 45 - 60 minutes |
| Full Dry | 48 hours |
| Fire Hazard Class | Non Flammable |

^{*}Coverage rates can vary according to the substrate porosity, texture and application method.

Performance Features and Benefits

Highly durable, Excellent resistance to fungal and algae growth, Free from harmful chemicals like APEO, formaldehyde, heavy metals etc, Low VOC content, Easy to apply and maintain, Superior washability & scrub resistance, Splendid coverage.

♦ Surface Preparation

The performance of this coating is directly related to the quality of surface Preparation.

- Ensure surface is clean, dry and free from oil, grease and other contaminants i.e. rust on metal.
- The surface should be rigid and sound.
- Wipe thoroughly with a damp cloth. In case of oil, grease or other contaminants, clean using a mild detergent or solvent, and rinse thoroughly with potable water to ensure complete removal of the contaminant and the detergent.

Application Tools

⊕

- Roller Recommended.
- Brush Recommended to paint corners and edges.
- Spray Use airless spray or conventional spray

Method of Application

- Application should be carried out with proper ventilation. Windows and doors should be kept open and maximum ventilation should be permitted for drying process.
- PinTura Cenomast Semi Gloss has to be stirred thoroughly prior to application.
- Prepared surface should be primed by applying one coat of Conmix ConDure Primer, applied using roller or brush.
- PinTura Cenomast Semi Gloss has to be applied between 6 to 24 hours after the application of the primer.
- Apply using a brush, roller or spray.
- A minimum of two coats should be applied to achieve the desired results.
- For Application by airless spray, use nozzle size "0.018 to 0.028" and pressure 2100 psi.
- Masking tape must be removed immediately after application of topcoat.

Conmix technical service team will assist in this procedure upon request.

♦ Recommended Paint System

- 1 x ConDure Primer
- 2 x PinTura Cenomast Semi Gloss
- 1 x ConDure Primer
- 2 x ConDure Stucco Filler
- 2 x PinTura Cenomast Semi Gloss
- ◆ Pack Size

1 USG & 5 USG

Shelf Life

18 months from date of production, provided the product is stored properly in original unopened packing under proper storage conditions.

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Container must be kept tightly closed.

Safety Information & Exposure Controls

Generally most of the water based paints are quite safe to handle with due precautions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Refer material safety data sheet as well.

General Information

Stir well prior to use.

Keep the container tightly closed to prevent drying.

Special Notes

Before painting the following aspect should be checked thoroughly:

- Moisture content of the wall (ideal condition below 10%)
- pH value of the wall surface (ideal condition below 11)

Application Tools

Paint Brush | Paint roller | Paint Spray

Method of Application

- Application should be carried out with proper ventilation. Windows and doors should be kept open and maximum ventilation should be permitted for drying process.
- PinTura Cenomast Gloss has to be stirred thoroughly prior to application.
- Prepared surface should be primed by applying one coat of Conmix ConDure Primer, applied using roller or brush.
- PinTura Cenomast Gloss has to be applied between 6 to 24 hours after the application of the primer.
- Apply using a brush, roller or spray.
- A minimum of two coats should be applied to achieve the desired results.
- For Application by airless spray, use nozzle size "0.018 to 0.028" and pressure 2100 psi.
- Masking tape must be removed immediately after application of topcoat.

Conmix technical service team will assist in this procedure upon request.

Recommended Paint System

1 x ConDure Primer

2 x PinTura Cenomast Gloss

1 x ConDure Primer

- 2 x ConDure Stucco Filler
- 2 x PinTura Cenomast Gloss
- Pack Size

1 USG & 5 USG

♦ Shelf Life

18 months from date of production, provided the product is stored properly in original unopened packing under proper storage conditions.

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Container must be kept tightly closed.

♦ Safety Information & Exposure Controls

Generally most of the water based paints are quite safe to handle with due precautions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately. Refer material safety data sheet as well.

General Information

Stir well prior to use.

Keep the container tightly closed to prevent drying.

Special Notes

Before painting the following aspect should be checked thoroughly:

- Moisture content of the wall (ideal condition below 10%)
- pH value of the wall surface (ideal condition below 11)