


6 X 25 (1+6+6+12)
 fils
 +
 1 Ame en textile



Diam. câble		Diam. fil ext.	Poids par 100 m	Charge de rupture effective mini*	Code art.
pouces	mm	mm	kg	kg	
5/16	8	0,55	32	4500	
3/8	10	0,6	37	6300	
	11	0,7	45	7650	
1/2	12	0,75	54	9100	
	13	0,8	63	10700	
9/16	14	0,9	73	12350	
5/8	16	1	95	16200	
	18	1,15	120	20500	
3/4	19	1,2	134	22890	
	20	1,25	148	25300	
7/8	22	1,4	187	29600	
	24	1,5	214	34500	
1	25	1,6	243	39200	
1 1/8	28	1,75	290	47800	
	30	1,8	308	50000	
1 1/4	32	2	379	61000	
1 3/8	36	2,2	476	78000	


*Classe 180/199/kg/mm²

Charge de rupture théorique = charge de rupture effective x 1.176

Utilisation :

- Traction, excavateurs.
- Déboisement.

6 X 25 (1+6+6+12)
 fils
 +
 1 Ame en acier



Diam. câble		Diam. fil ext.	Poids par 100 m	Charge de rupture effective mini*	Code art.
pouces	mm	mm	kg	kg	
5/16	8	0,55	35	4860	
3/8	10	0,6	41	6850	
	11	0,65	50	8300	
1/2	12	0,75	60	9850	
	13	0,8	70	11600	
9/16	14	0,9	80	13450	
5/8	16	1	105	17500	
	18	1,15	133	22200	
3/4	19	1,2	151	24700	
	20	1,25	164	27400	
7/8	22	1,4	205	32000	
	24	1,5	229	37600	
1	25	1,6	260	42800	
1 1/8	28	1,75	310	52000	
	30	1,85	347	57000	
1 1/4	32	2	405	66500	


*Classe 180/199/kg/mm²

Charge de rupture théorique = charge de rupture effective x 1.25

Utilisation :

- Appareils de chantier, pelles mécaniques
- Bulldozers, excavateurs
- Déboisement.

8 X 19 Filler
(8 x 25) (1+6/6F+12)
 fils
 +
 1 Ame en acier



Diam. câble		Diam. fil ext.	Poids par 100 m	Charge de rupture effective mini*	Code art.
pouces	mm	mm	kg	kg	
5/16	8	0,4	29	4430	
3/8	9	0,47	39	5500	
	10	0,52	44	6930	
7/16	11	0,58	53	8380	
15/32	12	0,63	63	9980	
1/2	13	0,68	74	11700	
9/16	14	0,72	86	13500	
19/32	15	0,78	99	15600	
5/8	16	0,82	109	17800	
11/16	17	0,88	127	20000	
23/32	18	0,92	140	22400	
3/4	19	0,98	160	25000	
25/32	20	1,03	177	27700	
7/8	22	1,15	214	33600	
15/16	24	1,25	255	39900	
1	26	1,35	299	46800	
1 1/8	28	1,45	345	54300	
1 1/4	32	1,65	450	70900	
1 3/8	36	1,85	570	89800	
1 1/2	40	2,05	705	111000	


*Classe 200/220/kg/mm²

Charge de rupture théorique = charge de rupture effective x 1.25

Utilisation :

- Ponts roulants.

6 x 26 WS
(1+5+(5+5)+10)
 fils
 +
 1 Ame en acier



Diam. câble		Diam. fil ext.	Poids par 100 m	Charge de rupture effective mini*	Code art.
pouces	mm	(mm)	(kg)	(kg)	
3/8	10	0,70	40	6900	
7/16	11	0,8	43	8400	
1/2	12	0,85	61	10300	
9/16	14	1	70	14200	
	15	1,05	91	15700	
5/8	16	1,15	107	18600	
	18	1,3	139	24300	
3/4	20	1,4	160	27800	
7/8	22	1,55	194	34200	
	24	1,65	218	38000	
1	25	1,8	256	45200	
1 1/8	28	2	315	56200	
	30	2,1	324	58700	
1 1/4	32	2,3	415	74400	
1 3/8	36	2,55	515	92500	

*Classe 180/199/kg/mm²

Charge de rupture théorique = charge de rupture effective x 1.25

Utilisation :

- Matériel de génie civil.
- Excavateurs, pelles mécaniques.
- Forage, mines et déboisement.